

POLYMER TYPE: POLYPROPYLENE HOMOPOLYMER

PACKING: PP bags of 25 kgs, 50 bags on a pallet shrunk by PE

APPLICATION: High stiffness thermoformed & injection moulded parts, special extrusion applications

PRODUCT FEATURES: Homopolymer with high stiffness

PROCESSING METHOD: Extrusion

Property	Test Method	Unit	Value
MFR (230° C/ 2.16 Kg)	ASTM D1238/L	gr/10min	6
Tensile Modulus of Elasticity (1mm/min)	ASTM D638	MPa	2000
Tensile Strength at Yield (50 mm/min)	ASTM D638	MPa	38
Elongation at Yield(50 mm/min)	ASTM D638	%	7
Notched Charpy Impact at 23°	ISO 179/ 1eA	KJ/m2	4
Notched Charpy Impact at -30°	ISO 179/ 1eA	KJ/m2	1.5
Vicat Softening Point, 10N	ASTM D1525	°C	158
Ball indentation hardness	ISO 2039-1	MPa	80
HDT (0.46 N/mm2)	ASTM D648	°C	108
Melting Point , DSC	ASTM D3417	°C	165

HOMOPOLYMER



**POLYMER
SELL**

RG 1002 L

The information in this publication is submitted without prejudice, and is based on our current knowledge and experience and on a limited number of tests. In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply and legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication".

IPS

POLYMER SELL

HOMOPOLYMER



www.polymersell.com
info@polymersell.com