

L2100TN00 is a heavy duty film grade produced by the tubular process without additives.

Properties	Unit	Typical value	Test Method
<b>Polymer Properties</b>			
Melt Flow Rate	dg/min	0.3	
Density	kg/m <sup>3</sup>	921	
<b>Optical Properties</b>			
Gloss (45°)	%	46	ASTM D 2457
Haze	%	12	ASTM D 1003A
Clarity	mv	65	SABTEC method
<b>Mechanical properties</b>			
Impact strength	KJ/m	35	ASTM D 4272
Tear strength (TD)	KN/m	25	
Tear Strength (MD)	KN/m	20	
<b>Tensile Test</b>			
Yield stress (TD)	MPa	11	
Yield stress (MD)	MPa	12	
Tensile Stress at break (TD)	MPa	26	
Tensile Stress at break (MD)	MPa	29	
Strain at Break (TD)	%	>500	
Strain at Break (MD)	%	>200	
Modulus of Elasticity (TD)	MPa	190	
Modulus of Elasticity (MD)	MPa	180	
Coefficient of friction		0.7	ASTM D 1894
Blocking	g	<5	
Re-blocking	g	30	

*LDPE*



### **Application**

Grade with excellent toughness and tear strength and outstanding shrink properties.very low energy consumption during processing and has excellent draw down ability.The material contains no additives and is suitable for application in shrinkhoods,industrial sacks,heavy duty carrier bags and liners.

### **General information**

LPC produces low density polyethylene by the tubular reactor process. As a result the product range covers a wide variety of densities and melt flow rates. The LDPE grade slate has a wide variety of slip and anti block additives levels and includes a large numbers of grades with excellent optical properties. LPC tubular production technology guarantees a very low gel level and outstanding draw down ability, low odor and taste levels, which is of advantage for thin film processing and e.g. food packaging.

### **Quality**

LPC is fully certified in accordance with the internationally accepted quality standard ISO 9001-2000.It is LPC policy to supply materials that meet customers specifications and needs and to keep up its reputation as a pre eminent, reliable supplier of e.g. polyethylene.

### **Environment**

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc.LPC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials.

### **Recycling**

Recycling of packaging materials is supported by LPC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered.Whenever ‘thermal’ recycling of packagings (i.e. incineration with energy recovery)is carried out, polyethylene –with its fairly simple molecular structure and low amount of additives-is considered to be a trouble-free fuel.

# LDPE



### **Food approvals**

The converter/food packager is responsible for compliance of the performance of the final article under foreseeable conditions of use. More specific information on the regulatory aspects of the LPC polyethylene is available in the relevant Food Approval Declarations which can be obtained from LPC Sales Office..

### **Safety**

Under normal conditions polyethylenes do not present a toxic hazard through skin contact or inhalation. During processing contact with molten polymer and inhalation of volatilized fumes should be avoided. It is recommended to install exhaust hoods over processing machines and to keep working area well ventilated. More specific information on the safety aspects of the LPC polyethylenes are provided in the relevant Material Safety Data Sheets, available from LPC Sales Office.

### **Storage**

As polyethylenes ,like most polymers, are combustible ,the usual precautions concerning ignition sources should be taken in warehouses and storage rooms. where large quantities are kept in store, it is necessary to observe the normal rules for orderly stock control and to keep out dust and moisture. Polyethylenes should be stored in such a way as to prevent exposure to direct sunlight, as this may lead to quality deterioration.

### **Disclaimer**

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties. It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate ,safe and legal use, processing and handling of all product(s) purchased from us. Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

# *LDPE*



## LDPE L2100TN00



# LDPE

