

## HDPE 62N11

**Application:**

Injection moulding grade for pallets and crates

**Feature:**

Characterisitics: Good Flowability, easy processing, high density, high rigidity

COMONOMER: -

ADDITIVES: Antioxidant, UV-Stablizer\*

Resin Property	Unit	Value	Method
Melt Index(190°C/2.16kg)	g/10min	11	ASTM D1238
Density(23°C)	g/cc	0.962	ASTM D1505
F/E Ratio	-	<30	ASTM D1238
Vicat	°C	133	ASTM D1525
Tensile Stress @ Yield	Mpa	32	ASTM D638
Tensile Stress @ Break	Mpa	15	ASTM D638
Elongation @ Break	%	200	ASTM D638
Flexural Secant Moduls	Mpa	1550	ASTM D790
Izod Impact Resistance	J/M	24	ASTM D256
Contamination	Ratio	<40	BASELL MTM-17064E

F/E: Ratio of MIF (190°C/2.16kg)/ MEI (190°C/2.16kg)

*HDPE*

